



Customer Coating Data Sheet

Liner Description/Color: Buff

Film Resin: Epoxy-phenolic

Use: Cover, Top, Body & Bottom

FDA Status: Compliant 175.300

Application Method: Roll coat or Airless Spray

Cure Temperature: 450°F PMT

Typical Uses

This coating has very good resistance to alkaline products and general solvents, but poor resistance to strong acids. The coating is more flexible than the straight phenolic systems. Products typically packaged with this coating include detergents, organic chemicals and surfactants.

Compatibility

Formulated products have different characteristics and do not always perform the same. In the absence of commercial packaging history, commodity testing is suggested to confirm liner and product compatibility. Testing should be conducted prior to commercial filling.