

Liner Description/Color: Rust inhibitor / Clear

Film Resin: Phenoxy & Epoxy

Use: Top, Body & Bottom

FDA Status: Compliant 175.300

Application Method: Roll Coat/Spray

Cure Temperature: 350°F PMT

Typical Uses

The purpose of the rust inhibitor coating is to prevent the interior surface of the pail from rusting prior to being filled. It is not intended to act as a lining.

Compatibility

Certain products may dissolve the rust inhibitor coating and contaminate the product. It is strongly suggested that compatibility tests be conducted to determine suitability.